

TREATED SILL PLATES, COLUMNS, AND STUDS

Featuring StrandGuard® TimberStrand® LSL

- Treated with zinc borate, using a proprietary process, for protection against insects and decay
- ICC ES accepted and meets AWPA treating standards for Use Category 2
- Treated throughout—no need to field treat after cutting or drilling
- Every piece is manufactured to be straight and true for fast installation and minimal waste
- Limited product warranty



TECHNICAL INFORMATION

Trus Joist® StrandGuard® TimberStrand® LSL Allowable Design Stresses (100% Load Duration)

		1.3E		1.5E	
		Beam Orientation	Plank Orientation	Beam Orientation	Plank Orientation
Modulus of elasticity	E =	1.3 x 10 ⁶ psi	1.3 x 10 ⁶ psi	1.5 x 10 ⁶ psi	1.5 x 10 ⁶ psi
Adjusted modulus of elasticity ⁽¹⁾	E _{min} =	660,750 psi	660,750 psi	762,400 psi	762,400 psi
Flexural stress	F _b =	1,700 psi ⁽²⁾	1,900 psi ⁽³⁾	2,250 psi ⁽²⁾	2,525 psi ⁽³⁾
Compression perpendicular to grain ⁽⁴⁾	F _{c⊥} =	680 psi	625 psi ⁽⁵⁾	775 psi	625 psi ⁽⁵⁾
Compression parallel to grain	F _c =	1,400 psi	1,400 psi	1,950 psi	1,950 psi
Horizontal shear parallel to grain	F _v =	400 psi	150 psi	400 psi	150 psi

(1) Reference modulus of elasticity for beam stability and column stability calculations, per NDS® 2005.

(2) For 12" depth. For other depths, multiply by $[\frac{12}{d}]^{0.092}$

(3) Value shown is for thickness up to 3½".

(4) F_{c⊥} may not be increased for duration of load.

(5) For sill plate applications only.

General Notes

- Zinc borate is an EPA-registered biocide.
- Accelerated testing (AWPA E12-94) indicates that adding zinc borate does not increase corrosivity. StrandGuard® treatment is less corrosive to fasteners and connectors than CCA or other copper-based alternatives.
- The StrandGuard® treatment process does not reduce design stresses for TimberStrand® LSL.
- For complete design and installation information regarding **wall framing** with TimberStrand® LSL, refer to the *Trus Joist® U.S. Wall Guide* for your region (Reorder TJ-9003 or TJ-9004).
- For complete design and installation information regarding TimberStrand® LSL **columns**, refer to the *Trus Joist® Beam, Header, and Column Specifier's Guide* (Reorder TJ-9000).

Connector Notes

Bolted Connections

- For bolts installed perpendicular to face and loaded parallel to grain, use a specific gravity of 0.50.
- For bolts installed perpendicular to face and loaded perpendicular to grain, use a specific gravity of 0.58.


Nailed Connections

- For lateral nail capacity, use a specific gravity of 0.50.
- For withdrawal nail capacity, use a specific gravity of 0.42 in the edge and 0.50 in the face.

Shear Walls

- When StrandGuard® TimberStrand® LSL sill plates are used in shear-wall construction, use the specific gravity of the studs when determining the allowable shear.
- Minimum edge nail spacing for 2x sill plate: one row at 4" on-center.
- Minimum edge nail spacing for 3x sill plate: two rows at 4" on-center, staggered.

WARNING: Drilling, sawing, sanding or machining wood products generates wood dust, a substance known to the State of California to cause cancer. For more information on Proposition 65, visit www.wy.com/inform.




StrandGuard® TimberStrand® LSL framing materials are intended for use in aboveground, protected applications such as sill plates, columns, and studs. The American Wood Protection Association (AWPA) standards classify such applications as Use Category 2.

StrandGuard® TimberStrand® LSL may be supported by masonry or concrete foundations, but must not come into contact with the ground, nor can it be substituted for studs in a treated-wood foundation.

For complete warranty information, see the limited warranty for StrandGuard® TimberStrand® LSL (Reorder #TJ-1005).

Product Storage



Protect products from sun and water

CAUTION:
Wrap is slippery when wet or icy

Use support blocks at 10' on-center to keep products out of mud and water

Code Evaluations:
See HUD MR 1265, ICC ES ESR-1387

Call your Weyerhaeuser representative today to order StrandGuard® TimberStrand® LSL. 1.888.453.8358

March 2012
Reorder TJ-8100

This document supersedes all previous versions. If this is more than one year old, contact your dealer or Weyerhaeuser rep.

▲, Weyerhaeuser, StrandGuard, TimberStrand, and Trus Joist are registered trademarks of Weyerhaeuser NR. © 2012 Weyerhaeuser NR Company. All rights reserved. Printed in the USA.